

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.


**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁵ : C08F 214/26, C09D 127/18	A1	(11) International Publication Number: WO 94/05712 (43) International Publication Date: 17 March 1994 (17.03.94)
(21) International Application Number: PCT/US93/07789 (22) International Filing Date: 24 August 1993 (24.08.93) (30) Priority data: 07/935,353 28 August 1992 (28.08.92) US 08/104,749 11 August 1993 (11.08.93) US (71) Applicant: E.I. DU PONT DE NEMOURS AND COMPANY [US/US]; 1007 Market Street, Wilmington, DE 19898 (US). (72) Inventors: CHAPMAN, George, Richard, Jr. ; 224 Wrights Lane, Media, PA 19063 (US). CRENSHAW, Lewis, Edward ; 1506 North Rodney Street, Wilmington, DE 19806 (US). McMINN, Rita, Sue ; 118 St. Regis Drive, Newark, DE 19711-3823 (US). MORGAN, Richard, Alan ; 4708 7th Avenue, Vienna, WV 26105 (US). PRIESTER, Donnan, Edwin ; 11 Swallow Hill Road, Greenville, DE 19807-1631 (US). STEWART, Charles, Winfield, Sr. ; 4 Jobs Lane, Newark, DE 19711-2314 (US). TUMINELLO, William, Howard ; 712 Fawn Road, Newark, DE 19711-2411 (US). TARNEY, Robert, Edward ; 505 Summit Drive, Hockessin, DE 19707 (US). VAN ALSTEN, John, Gregg ; 308 Hampton Road, Wilmington, DE 19803 (US). WAGMAN, Mark, Elliott ; 2519 Wexford Drive, Wilmington, DE 19810-1220 (US).		(74) Agents: TOCKER, Edwin et al. ; E.I. du Pont de Nemours and Company, Legal/Patent Records Center, 1007 Market Street, Wilmington, DE 19898 (US). (81) Designated States: CA, GB, JP, KR, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i>

(54) Title: LOW-MELTING TETRAFLUOROETHYLENE COPOLYMER AND ITS USES



(57) Abstract

Copolymers of tetrafluoroethylene (TFE) and hexafluoropropylene (HFP) having high HFP content and end-of-melting temperature, $T_m(\text{end})$, as low as 200 °C are disclosed. Exceptional performance as a processing aid in polyolefins results from having $T_m(\text{end})$ of the TFE/HFP copolymer close to the processing temperature of the polyolefin. These TFE/HFP copolymers are soluble in fluorinated cyclic solvents. Copolymer/solvent systems copolymer at significant concentrations in selected solvents are fluid and stable at room temperature.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	FR	France	MR	Mauritania
AU	Australia	GA	Gabon	MW	Malawi
BB	Barbados	GB	United Kingdom	NE	Niger
BE	Belgium	GN	Guinea	NL	Netherlands
BF	Burkina Faso	GR	Greece	NO	Norway
BG	Bulgaria	HU	Hungary	NZ	New Zealand
BJ	Benin	IE	Ireland	PL	Poland
BR	Brazil	IT	Italy	PT	Portugal
BY	Belarus	JP	Japan	RO	Romania
CA	Canada	KP	Democratic People's Republic of Korea	RU	Russian Federation
CF	Central African Republic	KR	Republic of Korea	SD	Sudan
CG	Congo	KZ	Kazakhstan	SE	Sweden
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovak Republic
CM	Cameroon	LU	Luxembourg	SN	Senegal
CN	China	LV	Latvia	TD	Chad
CS	Czechoslovakia	MC	Monaco	TG	Togo
CZ	Czech Republic	MG	Madagascar	UA	Ukraine
DE	Germany	ML	Mali	US	United States of America
DK	Denmark	MN	Mongolia	UZ	Uzbekistan
ES	Spain			VN	Viet Nam
FI	Finland				

TITLE

LOW-MELTING TETRAFLUOROETHYLENE COPOLYMER AND ITS USES

FIELD OF THE INVENTION

5 This invention is in the field of partially-crystalline tetrafluoroethylene copolymers having unusually low crystalline melting temperatures, which makes them useful in solution form and as aids for the extrusion processing of polyolefins, including polyolefins incorporating antiblock agents.

BACKGROUND OF THE INVENTION

Homopolymers of TFE are crystalline or partially-crystalline fluoroplastics. Copolymerization with other monomers that introduce side groups into the polymer affects the properties of the polymers. Generally, at low levels of comonomer incorporation, both melting
15 temperature T_m and crystallinity decrease with increasing comonomer content. Crystallinity is reflected, for example, by the heat of fusion per unit mass as determined by differential scanning calorimetry (DSC). At high levels of comonomer incorporation, all detectable crystallinity may vanish. If the monomers and their concentrations are properly chosen,
20 and molecular weight is properly controlled, useful fluoroelastomers or fluoroplastics may be obtained. For example, the TFE copolymer with perfluoro (methyl vinyl) ether (PMVE) in the approximate molar composition TFE/PMVE = 70/30 is a well-known fluoroelastomer. On the other hand, copolymers of TFE with HFP or perfluoro (propyl vinyl)
25 ether (PPVE) in the approximate molar compositions TFE/HFP = 92/8 and TFE/PPVE = 98.5/1.5 are well-known fluoroplastics. These particular perfluoroplastics have nominal T_m of about 260°C and 305°C, respectively, as judged by the peak of the melting endotherm by DSC. See Figure 1. The minimum T_m (peak) for fluoroplastics in these
30 compositional families recognized by ASTM standards is 250°C for TFE/HFP polymers (ASTM D-2116) and 300°C for TFE/PPVE polymers (ASTM D-3307). Such fluoroplastics have had commercial utility in part because of their relatively high T_m and the mechanical properties that accompany the level of crystallinity associated with relatively low
35 comonomer incorporation.

Partially-crystalline polymers are those which exhibit crystallinity under some conditions, as opposed to those polymers which are non-crystalline under all conditions. A partially-crystalline polymer typically exhibits crystallinity as polymerized, or after fabrication when the melted polymer is cooled slowly enough to permit development of molecular order. As is well-known, quenching from the melt can reduce or even preclude crystalline order in a specimen of a partially-crystalline polymer. The resultant quenched polymer is nevertheless considered partially crystalline because it started out, prior to melting and quenching, in this condition, and this condition is capable of being restored by reheating the polymer and cooling it more slowly. This effect is more likely for polymers with low crystallinity as polymerized. Crystallinity can be detected by several means, including differential scanning calorimetry (DSC).

There has been no interest in, and no commercial presence of, such fluoroplastics with comonomer concentration approaching but not reaching the level that completely eliminates crystallinity. The prior art does not exemplify TFE copolymers with perfluoroolefins having T_m below or even near 200°C.

Certain copolymers of tetrafluoroethylene (TFE) and hexafluoropropylene (HFP) are known. Bro & Sandt in U.S. Patent 2,946,763 disclose TFE/HFP copolymers with HFP content reflected by a specific infrared ratio, herein called HFPI or HFPI, in the range 1.5 to 6. They use a multiplier of 4.5 to convert HFPI to HFP content in wt%. Bro & Sandt teach that HFPI greater than 6 is extremely difficult to achieve. This is due to the low reactivity of HFP relative to that of TFE. An HFPI of 4.70 is the highest value exemplified. There are frequent references in the literature to TFE/HFP copolymers having HFP content of from 6.75 to 27 wt%, apparently following the disclosure of the 1.5 to 6 HFPI range and 4.5 multiplier by Bro & Sandt. U.S. Patents 4,075,362, 3,769,252 and Satokawa *et al* in U.S. Patent 3,904,575 refer to the TFE/HFP copolymers of U.S. Patent 2,946,763 for a teaching of a method of making such copolymers. The highest HFP content of any of the copolymers actually exemplified in the prior art is 25 wt% in U.S. Patent

4,075,362, corresponding to an HFPI of 5.56 according to the conversion factor of Bro & Sandt.

Khan & Morgan in U.S. Patent 4,380,618 uses a multiplier of 2.1 to convert HFPI into HFP content in mol%, so that the preferred
5 compositional range of 6 to 9 mol% corresponds to an HFPI of 2.86 to 4.29. In the examples for TFE/HFP copolymers in U.S. Patent 4,381,384, HFP content of 5.4 mol% corresponds to an HFPI of 2.57.

Fluoropolymers are known to be useful as processing aids when used in low concentration in other polymers to mitigate effects such as
10 melt fracture or high torque that limit rate of extrusion of these host polymers, thereby improving processibility. Polyolefins are a class of host polymers of particular interest. Blatz in U.S. Patent 3,125,547 teaches the use of fluoropolymers in polyolefins to facilitate extrusion. A general requirement taught by Blatz is that the fluoropolymer must be
15 molten or fluid at the processing temperature T_p of the polyolefin. Blatz exemplifies fluoroelastomers, which are non-crystalline and for which the glass transition temperature T_g is well below T_p , and, therefore, are fluid at T_p . Blatz also exemplifies tetrafluoroethylene (TFE) homopolymer which melts 55°C below T_p . There is no teaching about
20 how such fluoropolymers perform when an antiblock agent is present in the host polymer. A general problem with prior art processing aids is that the benefit of the aid is substantially reduced when an antiblock agent such as silica or talc is added to the polyolefin.

Smith & Gardner [Macromolecules 18, 1222 (1985)] review and
25 discuss dissolution of polytetrafluoroethylene (PTFE). They report that PTFE had been dissolved only in perfluorinated alkanes. In summary discussion, Smith & Gardner point out that many polymers analogous to PTFE and TFE copolymers, i.e., non-hydrogen-bonding polymers, dissolve only just below their melting points. There are no known
30 disclosures of solutions of melt-processible TFE/HFP copolymers of melt viscosity in the range 0.1×10^3 to 10×10^3 Pa·s. In particular, there are no known disclosures of such copolymer/solvent systems that are stable and fluid at room temperature.

SUMMARY OF THE INVENTION

It has been discovered that TFE/HFP copolymers having HFPI within a specifically selected range exhibit surprising utility as processing aids in polyolefins and as solutions in highly-fluorinated solvents. These copolymers have low crystalline melting temperature T_m due to unusually high HFP content. The unexpected benefit of these TFE/HFP copolymers as processing aids is attributed to the fact that, because of low T_m , T_m can be brought into register with common processing temperatures T_p for polyolefins. Solutions of these copolymers are fluid at significant concentrations at modest temperatures, including room temperature for selected copolymer/solvent systems, surprisingly so because T_m is so high above room temperature. The availability of solutions at modest temperatures enables TFE/HFP copolymers to be used in ways either not previously possible or at least inconvenient.

Specifically, this invention provides a TFE/HFP copolymer having an HFPI of 6.4 to about 9. Preferred for reasons of utility and/or ease of synthesis are those copolymers having HFPI in the range of about 7.3 to 9.0, and most preferably from 7.3 to 8.5. The invention also provides solutions of the copolymer in highly fluorinated solvents. Preferred solutions are based on solvents that permit dissolution of the TFE/HFP copolymer at atmospheric pressure and provide stable solutions at room temperature.

This invention also provides the use of the TFE/HFP copolymer, as well as other highly fluorinated polymers with similar melting points, as processing aids in polyolefins. It offers substantial benefit in the absence of antiblock agents and very little restriction in performance in the presence of antiblock agents. The highly-fluorinated polymers are partially-crystalline (as hereinbefore described) fluoroplastics with end of melting temperature $T_m(\text{end})$ in the range 180°-255°C, and preferably in the range 180°-235°C. When used as processing aids in polyolefins, copolymers are preferably chosen to have $T_m(\text{end})$ values close to the processing temperature T_p of the polyolefin. This range is from 40°C below T_p to 25°C above T_p , preferably from 30°C below to 15°C above

T_p , and most preferably from 20°C below T_p to 5°C above T_p .

Copolymers of TFE and HFP are preferred.

The invention also provides coatings of the TFE/HFP copolymer of the invention, and coated articles. When formed from solution,
5 coatings can be dense low-surface-energy films with thicknesses ranging down to 100 angstroms.

BRIEF DESCRIPTION OF THE FIGURES

Fig. 1 is a DSC trace for a prior-art TFE/HFP copolymer.

Fig. 2 is a DSC trace for a TFE/HFP copolymer of this invention.

10 Fig. 3 is a plot of the reduction in extrusion pressure of polyethylene without antiblock agent resulting from the use of TFE/HFP copolymers of this invention as processing aids in the polyethylene, vs. the difference between $T_m(\text{end})$ and T_p .

Fig. 4 is a plot of the reduction in extrusion pressure of
15 polyethylene containing an antiblock agent resulting from the use of TFE/HFP copolymers of this invention as processing aids in the polyethylene, vs. the difference between $T_m(\text{end})$ and T_p .

The lines in Figs. 3 and 4 represent the conclusions drawn from the data in the figures, and are not the result of a mathematical fit to the
20 data.

DETAILED DESCRIPTION OF THE INVENTION

TFE/HFP copolymers with low melting temperature T_m due to high HFP content have now been made by careful adjustment and control of several parameters in a semi-batch dispersion (sometimes
25 designated emulsion) polymerization process. These parameters include:

- 1) Extremely high HFP partial pressures in the range 83-95% of total monomer pressure.
- 2) Maintenance of the desired ratio of TFE and HFP monomers
30 throughout the batch by careful balancing of polymer formation and initiator solution addition against consumption of HFP monomer to keep the partial pressure of HFP constant.
- 3) Use of a surfactant type and amount that promotes the formation of numerous very small dispersion particles and thus a high
35 surface area for polymerization.

4) A dwell period of 10-30 min after full pressurization of the reactor, during which time no TFE is added beyond the precharged amount, to overcome a tendency to form TFE-rich copolymer early in the batch.

- 5) Reaction temperature as high as possible consistent with the problems or limitations recited above.

The TFE/HFP copolymers of this invention have HFPI in the range 6.4 to about 9. The HFPI range of about 7.3 to 9.0 is preferred, and the range 7.3 to 8.5 is most preferred. These copolymers have melt viscosity (MV) in the range 0.1×10^3 to 10×10^3 Pa·s, preferably 0.5×10^3 to 5×10^3 Pa·s.

The polymers of this invention may be made at least by the method known as dispersion (or emulsion) polymerization, and dispersion (or emulsion) polymerization in the presence of a solvent.

The minimum HFP partial pressure that can be used to make the TFE/HFP copolymer of this invention by the present semi-batch process is about 500 psig (3.4 MPa) out of 600 psig (4.1 MPa) total monomer pressure. HFP partial pressure is preferably about 525 psig (3.6 MPa), most preferably about 550 psig (3.8 MPa) out of 600 psig total monomer pressure. Higher, or slightly lower, total monomer pressure may be used, in which case HFP partial pressure should be adjusted proportionately.

The surfactant should be chosen to obtain high dispersion particle surface area (small particle size) in order to enhance reaction rate which is suppressed by the high concentration of HFP relative to TFE. The quantity required to achieve this objective will vary with the composition of the surfactant. A high concentration of surfactant can impede isolation of the TFE/HFP copolymer resin from the dispersion by some techniques. The concentration of surfactant should be less than 0.4 wt%, preferably less than 0.2 wt%, based on the aqueous medium. Suitable surfactants include ammonium perfluorononanoate, and the perfluoroalkyl ethane sulfonic acids and salts thereof disclosed in U.S. Patent 4,380,618. Of these, the mixture of C₆-C₁₆ perfluoroalkyl ethane sulfonic acids sold as Zonyl® TBS fluorochemical surfactant (Du Pont Company) is preferred.

Temperatures in the range of about 103°-108°C are suitable for making the TFE/HFP copolymers of this invention by the semibatch process used. In addition to the limitations of high-temperature polymerization outlined in the background section, surfactants used in emulsion polymerization appear to be less effective at temperatures above 103°-108°C and there is a tendency to lose dispersion stability.

Initiators commonly employed in emulsion polymerization of TFE copolymers are water-soluble free-radical initiators such as ammonium persulfate (APS), potassium persulfate (KPS), or disuccinic acid peroxide. APS and/or KPS is preferred.

After the reactor is charged with water, surfactant and monomers, heated to the chosen temperature, and agitation is started, a solution of initiator is added at a prescribed rate to initiate polymerization. It is preferred that pressure is allowed to drop as polymerization starts, and no TFE is added for a prescribed time, during which the initiator solution is continuously added. Then, TFE addition is started and controlled according to the scheme chosen to regulate the polymerization. It is possible to make a TFE/HFP copolymer with high HFP content without this dwell period, but the dwell period reduces the high-melting tail of the DSC trace, resulting in a narrower range of melting.

There are several alternatives for regulating the rate of FEP polymerization. It is common with most alternatives first to precharge all HFP monomer and then to add TFE to the desired total pressure. Additional TFE is then added after initiator injection and reaction kickoff to maintain the chosen pressure. The TFE may be added at a constant rate, with agitator speed changed as necessary to increase or decrease actual polymerization rate and thus to maintain constant total pressure. Alternatively, the total pressure and the agitator speed may both be held constant, with TFE added as necessary to maintain the constant pressure. A third alternative is to carry out the polymerization in stages with variable agitator speed, but with steadily increasing TFE feed rates. The latter two alternatives provide the most homogeneous product and are preferred.

The HFP monomer is much less reactive than the TFE monomer so that the HFP/TFE ratio must be kept high to assure a high incorporation of HFP. The polymerization kinetics under steady-state conditions also requires a constant ratio of the monomers throughout the polymerization in order to obtain a homogeneous copolymer, one with randomly distributed monomer units. Failure to do so will result in a broad HFP distribution and the resin will have a broad melting range. Since the TFE is much more reactive than HFP, careful maintenance of a constant HFP/TFE ratio is needed.

After polymerization and discharge of the copolymer dispersion from the reactor, the polymer may be isolated from the aqueous medium by one of the means well known in the art. One method is to stir vigorously until the polymer separates out as a non-water-wet powder which floats on the water and can be collected on a filter or decanted from the water. An electrolyte such as ammonium carbonate or nitric acid can be added to the dispersion to facilitate coagulation by the vigorous stirring. The polymer can be dried as collected or pressed to remove a portion of the water before drying. Another method is to stir the dispersion only until it thickens into a water-wet gel and then collect the polymer on a filter. The filtered polymer can be dried directly or can be washed with water or organic solvents such as methanol or acetone before drying. Pressing is not necessary because polymer collected in this manner is less prone to hold water droplets. Another method of isolation is spray-drying of the dispersion or the water-wet gel. Still another method of polymer isolation that can be used is the technique known as solvent-aided pelletization. In this method, the dispersion is first gelled either mechanically or chemically by the addition of an electrolyte such as ammonium carbonate or nitric acid. The gel is then broken by addition of a water-immiscible organic solvent with low surface tension, preferably not more than 35 dyne/cm, accompanied by agitation. Suitable solvents include hydrocarbon, halocarbon, and hydrohalocarbon liquids. If an agglomerating isolation technique is used, the temperature of the isolating process may influence the size or the friability of the resultant agglomerates.

Isolated wet polymer can be dried by any method suitable for drying finely divided solids. Air flow through the drying chamber should be consistent with the desire or any requirement to avoid blowing the powder about. The drying technique, temperature, and time chosen should be consistent with intended use of the dried polymer. If the polymer is to be used as a finely-divided powder, compaction of the powder mass and particle-to-particle fusion must be avoided. Since the TFE/HFP copolymers of this invention melt at unusually low temperatures, the drying temperature likewise must be low to obtain a free-flowing, finely-divided powder.

If the polymer is not to be used as a powder, higher drying temperatures can be used. If appropriate, conventional thermoplastic finishing techniques including extrusion formation of cubes or pellets can be used.

If stabilization of the TFE/HFP copolymer is required, one of several known techniques can be employed. These include, for example, the humid heat treatment of Schreyer (U.S. Patent 3,085,083), the extrusion-finishing of Morgan & Sloan (U.S. Patent 4,626,587), the chemical treatments of Bekiarian *et al* (U.S. Patent 4,946,902) and Buckmaster (U.S. Patent 5,045,605), and treatment with elemental fluorine. Some of these techniques would result in fusion of the polymer particles. The fused polymer can, of course, be ground if it is desired to have stabilized polymer in finely divided form. Treatment of polymer powder isolated and dried as described above with fluorine can reduce the number of unstable end groups, if their presence will be detrimental to the end use application, without destroying polymerization particle identity. The fluorination may be carried out with a variety of fluorine radical generating compounds, but the polymer preferably is contacted with fluorine gas. Since reactions with fluorine are very exothermic, it is preferred to dilute the fluorine with an inert gas such as nitrogen. Suitable conditions for fluorine treatment are those discussed by Buckmaster & Morgan in U.S. Patent 4,675,380, except that temperature should be between 0°C and the temperature at which the polymer particles begin to melt or fuse together if freely-flowing powder is

desired. This temperature may be as much as 50°-60°C below the peak melting temperature of the resin.

The TFE/HFP copolymers of this invention may have uses in dispersion form. In that case, the as-polymerized (raw) dispersion may be used as discharged from the reactor if it has adequate stability for the intended purpose. Alternatively, the raw dispersion can be stabilized by addition of surfactants, or concentrated and stabilized by techniques well known in the art.

The TFE/HFP copolymers of this invention can be in solution in highly fluorinated solvents. Because of their composition, they are unusually easy to dissolve and can provide stable, fluid copolymer/solvent systems at ambient temperature. Perfluorinated compounds are preferred as solvents, but fluorinated compounds having up to about 12.5 atomic percent (at%) hydrogen and/or about 37.5 at% chlorine can be used. Compounds most useful as solvents are highly fluorinated cycloalkanes or aromatics, both of which may contain fused or unfused rings. Highly fluorinated cycloalkanes are preferred. Both types of compounds may be substituted by perfluoroalkyl or perfluoroalkylene groups. For dissolution at atmospheric pressure, solvents with boiling points of about 140°C or greater are required. Under autogenous pressure, solvents with boiling points of about 70°C or greater are required. Compounds useful as solvents include, but are not limited to, perfluorodecalin, perfluoro(1-methyldecalin), perfluoro(dimethyldecalin), perfluoro(tetradecahydrophenanthrene), perfluoronaphthalene, perfluoromethylcyclohexane, perfluorobiphenyl, perfluoro(cyclohexylmethyl)decalin, and higher boiling adducts. Certain nitrogen-containing solvents such as perfluoro(triamylamine) may also be used. Preferred solvents are perfluorodecalin and perfluoro(tetradecahydro-phenanthrene).

Solutions can be prepared in a broad range of solvents at elevated temperature and under pressure. Solutions can be prepared at elevated temperature and at atmospheric pressure for a selected range of solvents with relatively high boiling points (BP). The temperature required for dissolution of the TFE/HFP copolymers varies with the solvent and the composition of the copolymer. For example, perfluorobenzene (BP =

80°C) readily dissolves a TFE/HFP copolymer of this invention under autogenous pressure at 85-90°C, but would not dissolve the polymer at atmospheric pressure. Perfluoro(tetradecahydrophenanthrene) (BP = 215°C) dissolves the same copolymer at about 115°C under autogenous pressure, but also can be used to prepare solutions at atmospheric pressure.

Solutions having concentrations of the TFE/HFP copolymer of this invention of as little as 0.1 wt% and as much as 10% and higher, 20% and 30% by weight, for example, can be made. Lower concentrations in the 0.1 or 0.5 to 10 and 0.1 or 0.5 to 5 and 0.5 to 2.5 wt% ranges are preferred for many purposes. Solution viscosity, of course, increases with polymer concentration. Solutions in selected solvents with polymer concentration in excess of about 2.5 wt% form gels when quiescently cooled to room temperature. Solutions at about 2.5 wt% and lower concentration in selected solvents form low-viscosity stable copolymer/solvent systems at room temperature. The exact nature of these fluid systems at or near room temperature is not known with certainty. They may be solutions, though sometimes subtle changes in optical properties may occur upon cooling. However, they may be microgels or colloidal dispersions. A copolymer/solvent system is considered to be stable if centrifuging does not substantially change the copolymer concentration in the solvent. This might occur even for a suspension, for example, if solvent and suspended particles had the same densities. The maximum concentration at which the system remains stable and fluid when quiescently cooled to room temperature in a particular solvent varies slightly with the composition of the TFE/HFP copolymer. Some solutions that form gels when quiescently cooled to room temperature can be kept fluid by shearing (stirring) while cooling. These latter systems may thicken with time, but remain pourable, and can be thinned again by restirring. The designation "copolymer/solvent system" is herein adopted to describe all of the fluid, stable systems of uncertain nature at and near room temperature. Solutions in certain other solvents precipitate and form low-viscosity suspensions when cooled to room temperature, and are useful as such. Selected copolymer/solvent systems with copolymer concentrations up

to about 2.5 wt% are easily sprayable at room temperature. Suspensions are sprayable at higher concentrations. The concentration of the copolymer in suspension can be at least 0.1 wt%, with the preferred compositions having the same copolymer concentrations as for the solutions. The concentrations of copolymer in the copolymer/solvent system will generally be about 0.1 to 10 wt%, and typically about 0.1 or 0.5 to 5 wt% or about 0.5 to 2.5 wt%.

All of these states of the copolymer associated with the solvent, if not already solutions at room temperature (20°C), can be returned to the solution state by heating of the system, preferably accompanied by stirring, and, if necessary, maintaining the resultant solution at an elevated temperature. Upon standing at room temperature, a small amount of solid material, possibly undissolved copolymer (may result from inadequate dissolving procedure) or contaminant might be discerned at the bottom of the solution. The same may be true for a suspension caused by some settling of the suspension to leave a top layer of solution. Thus, solution can be present along with settled solids and along with suspension. Agitation of these liquid media will redisperse the settled solids or suspension, as the case may be. Alternatively, these media can be subjected to filtration to remove all discernible solids, whereby solution will remain.

The TFE/HFP copolymers of this invention can be used in many ways. One use for which the melting temperature range of these selected TFE/HFP copolymers makes them surprisingly superior is as a processing aid in polyolefins. This aspect of the invention is discussed in detail below. The TFE/HFP copolymer resins can be used in powder or pellet form in any of the processes such as extrusion, molding, or pressing by which thermoplastics are conventionally fabricated into finished articles, providing the properties of the copolymer are suitable for the intended use. Such articles include filaments, film or sheet, tubing, hose, wire insulation, foamed structures including wire insulation, coatings on wire for mechanical uses, injection-molded items, blow-molded articles, bottles, containers, laboratory ware, protective linings, laminates and other composite structures, and the like. Certain of these articles, especially those with relatively small dimensions in at

least one direction such as tubing or film or bottles and made using rapid cooling from the molten state can have essentially no crystalline order, as discussed above. As a consequence, they can be transparent and substantially free from haze. Some laminates are essentially coated articles. The unique low-melting characteristics make the TFE/HFP copolymers of this invention suitable for uses not accessible to prior-art perfluoroplastics because properties were inappropriate or because required processing temperatures were too high. For example, a TFE/HFP copolymer of this invention can be used as a melt adhesive at moderate temperature. High processing temperatures of prior-art perfluoroplastics disqualified them for use in conjunction with many other materials which could not tolerate exposure to those temperatures.

In aqueous dispersion form, the TFE/HFP copolymers of this invention can be used according to any of the conventional techniques for using fluoropolymer dispersions, including coating, casting, and impregnation. Normally, after the copolymer dispersion particles are deposited in place in the wet state, the deposit is dried and the particles are fused thermally. Other materials can be blended into the TFE/HFP copolymer dispersions for these uses, or such blends can be co-coagulated as a step toward dry blends or filled resins.

The TFE/HFP copolymer solutions, suspensions, and copolymer/solvent systems of this invention can be used in many ways, making it possible to achieve end results that could not be achieved with previously available perfluoropolymers or could be achieved only in less convenient ways. These results include any of the results for which polymer solutions are used, such as coating, encapsulation, impregnation, and the casting of film. The TFE/HFP copolymer solutions, suspensions, and copolymer/solvent systems of the invention can be employed in any of the methods by which solutions are known to be used, including dipping, painting, and spraying.

The TFE/HFP copolymer solutions, suspensions and copolymer/solvent systems of this invention can be used to make coatings on a broad range of substrate materials, including metal, semiconductor, glass, carbon or graphite, and natural and synthetic polymers. The substrates can be in a broad range of physical forms,

including film or paper, foil, sheet, slab, coupon, wafer, wire, fiber, filament, cylinder, sphere, and other geometrical shapes, as well as in a virtually unlimited number of irregular shapes. Coatings can be applied by methods known in the art, including dipping, spraying, and painting.

- 5 For plane substrates of suitable dimensions, spin coating can be employed. Porous substrates can also be coated or impregnated. These include, for example, screens, foams, microporous membranes, and woven and non-woven fabrics. In making such coatings, the solvent can be driven off by heat leaving a dry, TFE/HFP copolymer coating. One
10 advantage of selected solutions or copolymer/solvent systems over aqueous dispersions for coating purposes is that coatings can be achieved below the melting temperature of the TFE/HFP copolymer. Another advantage is that extremely thin coatings can be achieved, as thin as 100 angstroms or possibly even thinner depending on the coating
15 characteristics required.

The TFE/HFP copolymer gels of this invention can be used to apply the copolymer to a site where it would be disadvantageous to use a low viscosity solution, suspension, or copolymer/solvent system.

- Coatings of the TFE/HFP copolymers of this invention can be a
20 sole coating on a substrate, or a component of a multilayer coating. For example, a TFE/HFP copolymer coating of this invention can be used as a first or primer, intermediate, or final coating in a multilayer fluoropolymer coating system. The coatings of this invention include coatings resulting from several successive applications of solution,
25 suspension, or copolymer/solvent systems to increase coating thickness to desired levels.

- Coatings of this invention can consist of the TFE/HFP copolymers of this invention alone, or of the TFE/HFP copolymers admixed with minor amounts of other materials either soluble in the
30 solvent or dispersed in the coating solution, suspension, or copolymer/solvent system. A minor amount can be up to about 10 wt% based on the combined weight of TFE/HFP copolymer and additive.

- Solutions can also be used to make microporous membranes from the selected TFE/HFP copolymers of this invention by conventional
35 solution immersion casting methods.

Specific coated articles are within the scope of this invention.

Coated articles include polymer extrusion dies and molds for rubber and plastic parts, such as o-rings, bottle caps, golf balls, golf ball covers, golf ball cover half shells, and the like. The TFE/HFP
5 copolymers of this invention both as-polymerized and after fluorine treatment can be used in coatings. In the case of dies used for extrusion of polyolefins, it is preferred that coatings be made from as-polymerized resin because such coatings are more durable. Both interior and exterior surfaces of extrusion dies may be coated to, respectively, facilitate
10 extrusion and alleviate die buildup.

Coated articles include gasoline engine carburetor parts; internal parts of internal combustion engines such as valves and piston skirts; razor blades; metal containers such as cans, pans, trays, vessels, and the like; metal sheets and foils; continuous metal belts; metal rods, tubes,
15 bars, profiles, and the like; bolts, nuts, screws, and other fasteners.

Coated articles include an article bearing a machine-readable marking on at least one surface, especially but not limited to a tag that can be attached to another object to provide information about inventory identification, contents, ownership, hazards, operating conditions, or
20 maintenance requirements, for example.

Coated articles include wire for electrical and mechanical service. In either case, the metal wire may be solid or stranded. Wires for mechanical service include catheter guide wire and the actuating wire of push-pull cable.

25 Coated articles include rubber o-rings, seals, beading, gasketing, and the like.

Coated articles include paper and textile materials, including woven fabric including glass fabric, non-woven fabric, felts, and the like, fibers including filaments, yarns, e.g. staple and continuous filament,
30 and strands.

Coated articles include foams, membranes, and the like.

Coated articles include optical fibers in which the substrate is a glass or plastic fiber.

Coated articles include semiconductors, semiconductor devices,
35 magnetic storage media including disks, photoconductors, electronic

assemblies, and the like, wherein the coating thickness may be as little as 200 angstroms or even as little as 100 angstroms or even as little as 50 angstroms. Use of solutions containing low concentrations of the TFE/HFP copolymer of this invention, e.g. as low as 0.001 wt%
5 copolymer can be especially advantageous to form these very thin coatings.

A coating of a composition comprising the TFE/HFP copolymer of this invention can be used as a melt adhesive to bond two articles together. The coating may be applied to a substrate from solution,
10 suspension, or stable copolymer/solvent system in a highly fluorinated solvent, from aqueous dispersion, or from thin film of the TFE/HFP copolymer to make a laminate, which is essentially a coated article. Two articles, at least one of which is a coated article comprising a substrate coated with the composition are brought together into conforming
15 contact such that one of the contacting surfaces is the coated substance. These two articles may in fact be a single article with two surfaces that are brought together, and more than two articles may be involved in the bonding, i.e., the bonding method of this invention is not limited to the bonding of two articles. After the two articles are brought together and
20 are in conforming contact with one another, at least the region of this contact is heated above the melting temperature of the copolymer. This heating can be begun prior to the articles being brought together. Pre-heating of the coated article or articles can be advantageous if the coating is applied from a hot solution of a high concentration of
25 copolymer in highly fluorinated solvent to avoid gel formation. With the articles in conforming contact, pressure is supplied to assure intimacy of contact for a time sufficient to effect the bond. This pressure can be an external force or can arise from the weight of the articles. The bonded articles ordinarily will be subsequently cooled to ambient
30 temperature.

As stated above, one use for which the melting temperature range of TFE/HFP copolymers of this invention makes them surprisingly superior is as a processing aid in polyolefins. Superior performance was unexpectedly found to be associated with the near coincidence of the
35 end of the melting temperature range for the TFE/HFP copolymer and

the processing (extrusion) temperature T_p for the polyolefin. As illustrated by examples to follow, the superior performance is not realized if copolymer melting ends either too far below T_p or too far above T_p . The desired end of melting is in a range from 40°C below T_p to 25°C above T_p , preferably from 30°C below to 15°C above T_p , and most preferably from 20°C below T_p to 5°C above T_p .

The surprisingly superior performance of the TFE/HFP copolymer of the present invention as a processing aid, attributed to the near coincidence of polyolefin processing temperature and the end of the melting temperature range of the processing aid, was found to extend to other highly-fluorinated partially-crystalline polymers. Specifically, the fluoropolymer processing aids of this invention can be copolymers of two or more fluoromonomers, with composition that places $T_m(\text{end})$ close to T_p . Suitable monomers include fluoroolefins and fluoroalkyl vinyl ethers. Preferred monomers include the perfluoroolefins TFE and $\text{CF}_2=\text{CFR}_f$, perfluoro (alkyl vinyl) ether $\text{CF}_2=\text{CFOR}_f$, and perfluoroalkyl ethylene $\text{CH}_2=\text{CHR}_f$, in which R_f is a perfluoroalkyl group with 1-5 carbon atoms. Limited amounts of hydrogen-containing monomers may be employed provided the hydrogen content of the polymer does not exceed about 2 wt%, and preferably does not exceed about 1 wt%. Especially preferred are perfluoropolymers, and in particular copolymers of TFE and HFP, optionally including minor amounts of other preferred monomers, and most especially the TFE/HFP copolymer compositions of this invention and discussed above. These partially-crystalline fluoropolymer processing aids may be used alone or in conjunction with other processing aids known in the art, including fluoroelastomers.

When the TFE/HFP copolymer of this invention is used as a processing aid in a polyolefin for film applications, the polyolefin generally will have a melt index (ASTM D-1238) of 5.0 or less at 190°C, preferably 2.0 or less. For high-shear melt processing such as fiber extrusion or injection molding, even high-melt-index resins, for example, those having a melt index of 20 or more, may suffer processing difficulties. Such polyolefins may comprise any thermoplastic hydrocarbon polymer obtained by the homopolymerization or

copolymerization of one or more monoolefins of the formula $\text{CH}_2=\text{CHR}'$ wherein R' is an alkyl radical, usually of not more than eight carbon atoms. In particular, this invention is applicable to the following: polyethylene, both of the high-density type and the low-density type
5 having densities within the range 0.89-0.97; polypropylene; polybutene-1; poly(3-methylbutene); poly(4-methylpentene); and linear low density copolymers of ethylene and an alpha-olefin, such as propylene, butene-1, pentene-1, hexene-1, heptene-1, octene-1, decene-1, octadecene-1, or n-methylpentene-1.

10 . Because of the different melt characteristics of the olefin polymers mentioned, the addition of the fluoropolymer process aids of this invention may be of greater value in some polyolefins than in others. Thus, polyolefins such as polypropylene and branched polyethylene, that have low molecular weight or broad molecular weight distributions
15 and, therefore, have good melt flow characteristics even at low temperature, may not require the use of the fluoropolymer additives or be noticeably improved by them, except under unusual, adverse extrusion conditions. However, for polymers such as high molecular weight, high density polyethylene or linear low density ethylene
20 copolymers, particularly those with narrow or very narrow molecular weight distributions, addition of the fluoropolymers is especially beneficial.

Such polyolefins are typically processed by extrusion techniques at melt processing temperatures T_p in the range 175°-275°C. The
25 commercially important blown-film process is usually carried out at T_p in the range 200°-250°C, and commonly at 200°-230°C. T_p in these blown-film processes is below, and in the lower range is substantially below, T_m of prior art TFE/HFP copolymer resins as discussed above. Thus, these prior art resins would be solid at T_p as described in U.S.
30 4,904,735.

The polyolefins and thus the polymer blend composition containing the fluoropolymer processing aid may contain assorted additives used in the art, such as but not limited to antioxidants, acid scavengers, light stabilizers, pigments, slip agents, and lubricants. In

particular, finely divided solids such as silica or talc may be incorporated as antiblock agents.

It is important for effective performance as a processing aid that the fluoropolymer resin be well-dispersed in the host resin. Although
5 precise quantitative characterization is not possible, it appears desirable that a significant fraction of the fluoropolymer resin be dispersed in the host with fluoropolymer particle size of less than about 0.5 μm and preferably less than about 0.3 μm . Since the raw dispersion particle size
10 obtained in polymerization is typically 0.05-0.2 μm , little agglomeration is desired. Therefore, for processing aid use, techniques chosen for isolation of the fluoropolymer resin from the raw dispersion should be among those that preserve the fundamental particle character or yield loose agglomerates that are readily dissociated upon incorporation into the host resin.

15 For effective performance as a processing aid, the melt viscosity (MV) of the fluoropolymer should be neither too low nor too high. For highly fluorinated partially-crystalline fluoropolymers in general, the MV range 0.1×10^3 to 20×10^3 Pa·s is suitable and the range 0.5×10^3 to 15×10^3 Pa·s is preferred. For the TFE/HFP copolymers of this
20 invention (HFPI of 6.4 to about 9), the MV range 0.1×10^3 to 10×10^3 Pa·s appears to be suitable. It appears that, as the MV of the TFE/HFP copolymer resins decreases, such resins become less effective as processing aids in the presence of antiblock agents as the difference between T_p and $T_m(\text{end})$ increases. Accordingly, a minimum MV of 0.5×10^3 Pa·s is preferred and the MV range 0.5×10^3 to 5×10^3 Pa·s is most
25 preferred for these copolymers. The fluoropolymer of the blend composition preferably has a $T_m(\text{end})$ from about 180°C to about 255°C, and more preferably from about 180°C to about 235°C.

The concentration of fluoropolymer processing aid in the host
30 resin at fabrication into the final article should be high enough to achieve the desired effect in improving processibility, but not so high as to have adverse economic impact. The amount required can vary with the effect desired, the host resin, additives used in the host resin, and the processing conditions which may be different from the laboratory
35 conditions reported in the following examples. Under certain

conditions, concentrations of 100 ppm or less, as low as 50 ppm or even 25 ppm, can be effective. Under other conditions, the effective amount may be 1000, 2000, or even 5000 ppm. For special purposes, concentrations of 10% or even 25% may be appropriate. Thus from
5 about 25 ppm to about 25% by weight of the fluoropolymer may be present, with preferred ranges being from about 100 ppm to about 10% by weight, and even more preferable, about 100 ppm to about 2000 ppm by weight of the fluoropolymer. The fluoropolymer processing aid can be incorporated into the host resin at the desired final concentration, or
10 can be incorporated into a masterbatch or concentrate that is added to the host resin in a ratio calculated to yield the desired final concentration. When the fluoropolymer is a TFE/HFP copolymer and a masterbatch is to be made, it is advantageous to subject the copolymer powder to fluorine treatment. Alternatively, it is advantageous to use
15 copolymer isolated from its polymerization medium by a technique comprising the use of a high concentration of salt-type electrolyte such as ammonium carbonate or potassium fluoride. In either case, the effectiveness of the masterbatch is enhanced.

20

EXAMPLES

The evaluations reported in the following examples were made using a C. W. Brabender Instruments, Inc. Computerized Plasti-Corder® equipped with a 19.1-mm (0.75-inch) extruder with a 25/1
length/diameter ratio. The screw had 10 feed flights, 10 compression
25 flights with a 3:1 compression ratio, and 5 metering flights. Operating parameters were controlled by four independent heating zones, four pressure transducers, and a torque measuring drive unit with 1-120 rpm capability. The instrument was equipped with software for rheometric extrusion testing. The extrusion head used for these tests was a
30 horizontal ribbon (tape) die body, supplied by C. W. Brabender, made from #416 ferritic stainless steel and designed to accept die inserts such that the exit width was 2.54 cm (1.0 inch), the land length was 1.016 cm (0.4 inch) and the die gap was a nominal 0.508 mm (0.02 inch). Die inserts used were chrome-plated tool steel. The die inserts were cleaned
35 prior to each evaluation by either scrubbing with a Scotchbrite® pad (3M

Company) and washing with acetone, or by scrubbing with a Scotchbrite® pad, washing with acetone, and burning.

In operation, the required machine conditions were set, and the polymer resin was extruded, usually at 60 rpm, until equilibrium was reached as judged by constant throughput and constant die pressure. For a linear low density polyethylene (LLDPE) with a melt index (MI) of 1.0 at 190°C, extrusion at 60 rpm at 200°C measured at the die gave a throughput of about 25-28 g/min and a die pressure of about 19-30 MPa (2800-4300 psig), depending on the exact die gap. As will become apparent, various extrusion temperatures were employed depending on the fluoropolymer being tested. Throughput and die pressure will, of course, change with temperature. Experiments were carried out using the following sequence of feed resin: first polyolefin resin without fluoropolymer or antiblock agent, second resin containing fluoropolymer process aid, and third resin containing both fluoropolymer process aid and antiblock agent. When equilibrium was reached for each composition, unless otherwise stated, a sequence of screw speeds was employed producing new equilibrium values of throughput and die pressure at each speed. Surface quality of the extrudate was judged by visual examination.

When changing the feed composition, the initial output parameters corresponded to the previous equilibrium, and then gradually changed to a new equilibrium. In the examples that follow, when switching from the natural polyolefin to the blend containing fluoropolymer, the Brabender feed hopper was run empty (or vacuumed out). The blend containing the fluoropolymer process aid was prepared by shaking the components vigorously in a polyethylene bag for approximately two minutes. The blend was then put into the feed hopper. A similar procedure was followed in switching from polyolefin feed containing fluoropolymer process aid to polyolefin feed containing fluoropolymer and antiblock agent.

The performance of a particular fluoropolymer as a processing aid was characterized as follows. For each feed composition and chosen melt processing temperature T_p , extrusion was carried out for a sequence of screw speeds, usually 30, 60, 90 and 120 rpm. Throughput

and die pressure p were recorded. From this data set, standardized values of p at five throughput values, usually 15, 20, 25, 30 and 35 g/min, were calculated by linear interpolation between the two bracketing data points. Pressures are designated p_o for the natural polyolefin, p_1 for the polyolefin with fluoropolymer process aid, and p_2 for the polyolefin with fluoropolymer and antiblock agent. The performance of a fluoropolymer is characterized by the pressure differences Δp_1 and Δp_2 which are the averages, respectively, of the quantities $\Delta p_{1i} = (p_{oi} - p_{1i})/p_{oi}$ and $\Delta p_{2i} = (p_{oi} - p_{2i})/p_{oi}$ calculated for the five throughput values i . Large values of Δp_1 and Δp_2 , and Δp_2 comparable to Δp_1 , are desired.

T_p was recorded both as the die temperature set point and the melt temperature at the die. Melt temperature may differ from die temperature set point by a few degrees. Melt temperature may also vary slightly with screw speed. The single temperature reported as T_p in the examples is the die temperature set point.

After each series of examples, the die inserts were removed and the extruder and die body were purged extensively using a 50/50 blend of LLDPE with MI = 1.0 and a 20% silica masterbatch, followed by 100% of the same LLDPE. Replacement die inserts were prepared and installed. After calibration of the transducers, the natural polyolefin resin was run to establish equilibrium conditions and to assure that reliable data were being obtained. If previously established equilibrium values for the natural resin were not achieved, the cleanout procedure was repeated. Alternatively, the extruder and die body were completely disassembled and the screw, barrel, die assembly, transducers, and thermocouples were thoroughly cleaned, first with a motor-driven brass brush and finally with acetone solvent. An extrusion test for equilibrium values was then carried out as described above.

The polyolefin resin used both for testing and purging was GRSN 7047, an LLDPE with MI = 1.0 in granular form from Union Carbide Corp.

Unless otherwise specified, the antiblock agent used was Super Floss® silica (Manville Sales Corp.) as a 20 wt% masterbatch in low density polyethylene with MI = 9.0 (masterbatch obtained from Ampacet

Corp.) The silica concentration in the final extrudate was 5000 ppm. This same masterbatch was used as the purge compound.

Melting characteristics of fluoroplastics were determined by DSC by the method of ASTM D-4591-87, except that the end of the melting range, here designated $T_m(\text{end})$, was determined according to the general method ASTM E794-85. $T_m(\text{end})$ is regarded as the temperature at which the entire specimen is melted. Figure 1 shows the DSC melting trace for a commercial TFE/HFP copolymer resin of Type I in ASTM D-2116-83. The width of the melting endotherm may be due to a distribution of polymer composition in the sample. Heat of fusion for Type I copolymer is about 20-24 J/g. Figure 2 shows the DSC trace for an experimental TFE/HFP copolymer resin with higher HFP content and consequently lower melting temperature range than the copolymer of Figure 1. Crystallinity is also lower as indicated by lower heat of fusion, about 10.5 J/g. For TFE/HFP copolymers with $T_m(\text{peak}) = 170^\circ\text{--}180^\circ\text{C}$, heat of fusion is typically 8-14 J/g. Since thermal history can affect crystallinity, DSC specimens were dried at temperatures no higher than 100°C .

Fluoropolymer compositions were determined by infrared spectroscopy on 0.025-0.051 mm thick films pressed at 300°C . For TFE/HFP copolymers, Fourier transform infrared spectroscopy was employed in the method described in U.S. Patent 4,380,618. In applying this method, the peak absorbances of bands found at about $10.18\ \mu\text{m}$ and at about $4.25\ \mu\text{m}$ were used, not the absorbances at these exact wavelengths unless they were also the peak absorbances. HFP content is expressed as an index HFPI, the ratio of the two peak absorbances. Multiplication of HFPI by 2.1 would yield the HFP content in mol% according to current calibration by ^{19}F NMR.

Quantitative measurement of carboxylic acid and acid fluoride end group populations in the TFE/HFP copolymers of this invention were carried out by infrared analysis (Nicolet model 5DX instrument) on films approximately $250\ \mu\text{m}$ thick which were cold-pressed from the dried copolymer powders, following the general method taught in U.S. Patent 3,085,083. Calibration factors (CF) were determined by measuring the absorptivities of model compounds containing the end

groups of interest. The levels of endgroups were then calculated by the equation:

$$\text{End groups per } 10^6 \text{ C atoms} = \frac{\text{absorbance} \times \text{CF}}{\text{film thickness}}$$

where film thickness is in μm .

The absorbance at $5.31 \mu\text{m}$ attributed to acid fluoride end groups was employed with a CF of 669. Analysis of high levels of acid end groups can be a particular problem since absorbances for bonded and free acid ends at 5.64 and $5.52 \mu\text{m}$ tend to overlap. For this work, the absorbance for free acid ends at $2.81 \mu\text{m}$ was employed with a CF of 787. Other work has shown that the absorptivities at 5.64 and $5.52 \mu\text{m}$ for the two acid structures are nearly the same, so the level of bonded acid end groups was determined by taking the ratio of these two absorbances and multiplying the ratio by the level of free acid end groups obtained from the $2.81 \mu\text{m}$ absorbance.

Melt viscosities of the partially-crystalline fluoropolymers were determined by ASTM method D1238-52T modified as described in U.S. Patent 4,380,618, except that a weight of 833 g was used for samples with MV below about $10^3 \text{ Pa}\cdot\text{s}$.

Example 1

A cylindrical, horizontally disposed, water-jacketed, paddle-stirred, stainless steel reactor having a length to diameter ratio of about 1.5 and a water capacity of 79 parts by weight was charged with 48.5 parts of demineralized water. The reactor was heated to 65°C , evacuated, purged with TFE, and then evacuated again. The vacuum in the reactor was then used to draw in a solution of 0.055 parts of Zonyl® TBS surfactant in water (1.8 parts). The solution was rinsed into the reactor with another 0.88 parts of water. The reactor was then sealed, agitation was begun at 38 rpm, and the reactor temperature was raised to 103°C . After the temperature had become steady at 103°C , HFP was added slowly to the reactor until the pressure was 545 psig (3.8 MPa). Then TFE was added to the reactor to achieve a final pressure of 600 psig

(4.1 MPa). Then 1.32 parts of a freshly prepared 0.45 wt% aqueous solution of ammonium sulfate (APS) initiator were pumped into the reactor at 0.11 part/minute. Thereafter, a 0.93 wt% APS solution was added to the reactor at 0.022 part/minute was added to the reactor for the remainder of the polymerization. After polymerization had begun as indicated by a 10 psig (0.07 MPa) drop in reactor pressure, additional TFE was added to the reactor to maintain pressure constant at 600 psig and agitator speed was increased to 50 rpm and held essentially constant for the remainder of the batch. No dwell period was used, and 0.3 part of TFE was added during the first 20 min after polymerization had begun. Total TFE added to the reactor in 403 minutes after initial pressurization was 14.5 parts. The agitator was then turned off, the TFE feed was stopped, and the reactor was cooled. When the temperature reached 90°C, the reactor was vented and the initiator feed was stopped. After venting to nearly atmospheric pressure, the reactor was purged with nitrogen to remove residual monomer. The dispersion was then discharged from the reactor and coagulated by vigorous stirring to obtain a TFE/HFP copolymer powder which was dried in a vacuum oven at 100°-120°C before being characterized. The resin had an MV of 0.6×10^3 Pa-s, an HFPI of 8.87, a $T_m(\text{peak})$ of 171°C, and a $T_m(\text{end})$ of 204°C.

Example 2

The reactor and charging procedure described in Example 1 were employed to add a total of 50.7 parts demineralized water and 0.081 part of Zonyl® TBS surfactant. After sealing the reactor, the agitator was turned on at 38 rpm and the reactor temperature was raised to 108°C. After the temperature had become steady at 108°C, HFP was added slowly to the reactor until its pressure was 550 psig (3.8 MPa). Then TFE was added to the reactor to achieve a final pressure of 600 psig (4.1 MPa). Then 0.66 part of a freshly prepared aqueous solution containing both 0.85 wt% APS and 1.32 wt% KPS was added at a rate of 0.033 part/min for 20 minutes. Polymerization began during this 20 minutes as indicated by a 17 psig (0.12 MPa) drop in reactor pressure.. No TFE was added during this 20 minute interval. At the end of the 20 minutes, the pressure was brought back to 4.1 MPa by the addition of 0.2 part of

TFE. The remainder of the polymerization was carried out with TFE and initiator solution (0.24 wt% APS and 0.36 wt% KPS) additions as indicated below. The agitator speed was varied as needed to achieve the TFE feedrates shown below.

5			
	<u>Time Period</u>	<u>TFE Feedrate</u>	<u>Initiator Feedrate</u>
	<u>(min)</u>	<u>(part/min)</u>	<u>(part/min solution)</u>
	First 80	0.024	0.0154
10	Next 60	0.032	0.0176
	Next 70	0.040	0.0198
	Next 70	0.050	0.0242
	Next 60	0.061	0.0286

- 15 After the TFE addition indicated above was complete, the reactor was cooled and vented, and the dispersion was discharged from the reactor as described in Example 1. The dispersion had 26.9 wt% solids. The raw dispersion particle size was 0.07 μm by photon correlation spectroscopy. A portion of the dispersion was cooled to 20°C and was then coagulated
- 20 by vigorous stirring to obtain a powder which was dried in a vacuum oven at 100°C. Analysis indicated the TFE/HFP copolymer resin to have an MV of 1.7×10^3 Pa·s, an HFPI of 8.34, a $T_m(\text{peak})$ of 166°C, and a $T_m(\text{end})$ of 201°C.

Example 3

- 25 A 5 wt% solution of a TFE/HFP copolymer synthesized by the procedure of Example 1 and having HFPI = 8.30, $T_m(\text{peak})$ = 170°C and MV = 0.2×10^3 Pa·s was made by the following procedure at ambient pressure. Into a 50 ml Erlenmeyer flask were placed 1.6 g of TFE/HFP copolymer resin and 28.5 g of perfluoro(tetradecahydrophenanthrene),
- 30 $\text{C}_{14}\text{F}_{24}$ (Flutec® PP11, Rhone-Poulenc). The loaded flask was placed in a silicone oil bath at 160°C and stirred with a glass-coated magnetic stirrer bar. Dissolution was complete in about 30 minutes. A reflux condensor was not necessary since the wall of the flask was cool enough to condense the solvent. Upon cooling to room temperature, the solution
- 35 formed a clear gel which readily redissolved upon warming to about 105°C.

Example 4

Solutions of the TFE/HFP copolymer used in Example 3 were made under autogenous pressure in four different solvents. Borosilicate glass tubes with 8-mm outside diameter and 1-mm wall were sealed at one end. Solvent and polymer powder were then introduced in proportions to provide a 5 wt% solution of polymer in solvent. Enough solvent and polymer powder were placed in the tubes so that, when the tubes were sealed with final lengths of 7.5-10 cm, solvent and polymer powder together occupied about half of tube volume. The tubes were then placed in holes in an aluminum block that was suitably heated and insulated. Other holes in the block served as viewing ports to observe the dissolution process in the tubes. Temperature was measured by three thermocouples placed within a few mm of the tube at different positions along the tube and could be controlled to $\pm 0.5^{\circ}\text{C}$.

The temperature was increased at a rate of about $1^{\circ}\text{C}/\text{min}$ until the polymer powder dissolved. Dissolution was judged visually, and the temperature at which dissolution was complete was designated T_D . Once dissolution occurred, the block was cooled in 5°C increments. By tilting the block and observing the solution behavior, the temperature T_C at which recrystallization occurred was estimated from the point of significant viscosity increase or the onset of turbidity. Likewise, upon reheating in 5°C increments, the temperature T_M (the solution melting point) at which complete dissolution occurred on reheating, was estimated from the point of significant viscosity decrease or the loss of turbidity. Solvents used and the results are shown in Table 1.

Table 1. TFE/HFP Copolymer in Different Solvents

<u>Solvent</u>	<u>T_D (°C)</u>	<u>T_C (°C)</u>	<u>T_M (°C)</u>
C ₆ F ₆ ^a	85-90	75	88
C ₇ F ₁₄ ^b	155	115	155
C ₁₀ F ₁₈ ^c	100-125	75-100	100-125
C ₁₄ F ₂₄	115	80	113

^a Hexafluorobenzene^b Perfluoro(cyclohexane)^c Perfluorodecalin**Example 5**

The procedure of Example 4 was followed to dissolve the TFE/HFP copolymer of Example 3 in C₁₄F₂₄ at three different concentrations. Results shown in Table 2 suggest greater solution stability at lower polymer concentration.

Table 2. Concentration Dependence of Solubility

<u>Polymer (wt%)</u>	<u>T_D (°C)</u>	<u>T_C (°C)</u>	<u>T_M (°C)</u>
1	105	45-50	87
5	110-120	85	103
10	130	110	120

Example 6

An aliquot of the TFE/HFP copolymer used in Example 3 was treated with fluorine to reduce the population of polymer acid end groups from 10¹⁰/10⁶ carbon atoms as-polymerized to 110/10⁶ carbon atoms. Fluorine treatment may also reduce the concentration of any residual surfactant. For a 5 wt% solution in C₁₄F₂₄ made by the procedure of Example 4, results were T_D = 160°-165°C, T_C = 155°C, and T_M = 160°-165°C. These values are all distinctly higher than the values in Examples 4 and 5 for the same polymer before fluorine treatment. DSC showed no significant difference between the as-polymerized and the fluorinated samples. Since C₁₄F₂₄ is not a polar solvent, it is difficult to explain the differences in solution behavior.

Example 7

- A 5 wt% solution identical to that of Example 3 was prepared by the procedure of Example 3 except that the temperature of dissolution was 150°C. The solution gelled when cooled to room temperature, but
5 was readily restored when reheated. New die inserts for the C. W. Brabender extruder described above were cleaned with acetone, heated to about 150°C, and dipped in the solution at 150°C. The solution was observed to wet the die inserts uniformly. Excess solution was allowed to drain off, and the inserts were baked in an oven for 2 hr at 200°C.
10 Under visual inspection, the copolymer coating on the die inserts appeared to be uniform and smooth with no uncoated areas. Water dropped on the inserts formed beads. The coated die inserts were used in a test extrusion of GRSN 7047 LLDPE at 60 rpm and 220°C. Extrudate at startup was clear with no melt fracture, and the die pressure was
15 immediately about 50% of the value obtained with uncoated inserts under the same conditions.

Example 8

- A 5 wt% solution of a TFE/HFP copolymer with HFPI = 8.81 and $MV = 1.2 \times 10^3$ Pa·s in $C_{14}F_{24}$ was prepared by the procedure of Example
20 3, except that dissolution temperature was 150°C. Copper, brass, aluminum, stainless steel, and galvanized steel coupons (2.5 cm x 12.5 cm x 0.6 mm, approximately) were cleaned with acetone and dipped at ambient temperature into the solution at 150°C. Excess solution was drained off and the metal pieces were baked overnight in an oven at
25 300°C. Coating quality was good as judged by visual inspection and as demonstrated by water non-wetting. Adhesion of coatings to the metals was good as judged by difficulty in scraping off the coatings with a laboratory knife.

Example 9

- Solutions at 5, 3, and 1 wt% were prepared as in Example 8. The 3
30 and 5 wt% copolymer/solvent system both gelled when cooled to room temperature, but the 1 wt% solution remained fluid. Glass microscope slides were washed with acetone, dried, and dipped at ambient temperature into the three solutions maintained at 150°C. Excess
35 solution was drained off and different slides were baked overnight at

150°, 200°, or 250°C. No differences were noted in appearance or in adhesion as judged by probing and scraping with a laboratory knife. However, under optical and scanning electron microscope examination, coating uniformity appeared to improve with solution concentration.

5 Separately, it was established that 2.5 wt% is the approximate concentration limit at which solutions of this copolymer resin in C₁₄F₂₄ remain as stable and fluid copolymer/solvent systems at ambient temperature, and may be applied to substrates by spray techniques. Centrifuging did not change the concentration of TFE/HFP copolymer
10 in the C₁₄F₂₄.

A 1 wt% solution of this same copolymer in perfluorodecalin (C₁₀F₁₈) formed a stable copolymer/solvent system at room temperature. The concentration limit for room temperature stability in C₁₀F₁₈ was not determined.

15

Example 10

Solution A was prepared as in Example 8, except that concentration was 2.5 wt%. Solution B was prepared as in Example 8, except that the solvent was predominantly perfluoro(triamylamine) (Fluorinert® FC-70 from 3M). When cooled to room temperature, the
20 latter solution became a cloudy suspension but did not gel. Agitation indicated that viscosity was low and was judged similar to that of FC-70. After centrifuging, the concentration of TFE/HFP copolymer in the FC-70 was essentially zero, confirming a suspension.

System A and suspension B, and a standard mold release (No. 25 1725, McLube) were sprayed at room temperature onto different sectors of a mold for size 214 o-rings. Preheated molds were found to yield the same results as molds at room temperature when sprayed. The sprayed mold was held empty in a press at 177°C for about 15 minutes. Then, a compound based on a perfluoroelastomer of the type disclosed in U.S.
30 Patent 4,035,565 was press-cured at 177°C for 15 min in the mold in a series of moldings. Results were about the same for o-ring cavities sprayed with system A and suspension B. For the first cycle, o-rings had a matte finish with excess TFE/HFP polymer resin on the surface. For the second cycle, the o-rings were glossy with some surface
35 imperfections. For the third cycle, the o-rings had high gloss. The o-

rings released from the mold equally well for all three cycles, popping out with very little prodding to loosen them. For the cavities sprayed with the conventional mold release, more effort was needed to remove the o-rings from the mold.

5

Example 11

A room-temperature copolymer/solvent system identical to the 1 wt% system of Example 9 was used. The copolymer/solvent system was sprayed, using an aerosol sprayer ("Sure Shot Aerospray", Milwaukee Sprayer Mfg. Co.), onto a hot (177°C) chrome-plated 12-cavity compression mold for AS 568-214 o-rings. The coated mold was placed in a circulating air oven for 30 min at 250°C, and was then moved to a laboratory press for molding tests. Two carbon-black-filled fluoroelastomer compounds designed for o-ring service were each molded in six press-cure cycles of 4 min at 177°C in the coated mold.

15 The first compound molded was based on a fluoroelastomer of the type disclosed in U.S. Patent 3,051,677 and incorporated a polyol curing system. O-ring release was good for the first molding cycle, then appeared to improve during the second and third cycles and level off for the remainder of the six cycles with this compound. The second

20 compound molded was based on a fluoroelastomer of the type disclosed in Comparative Example A of U.S. Patent 4,973,633 and incorporated a peroxide curing system. O-ring release was good for the first cycle, but became progressively more difficult throughout the remainder of the six cycles with this compound.

25

Example 12

The solution of Example 8 was used. Pieces of cured ethylene/propylene/diene-monomer (EPDM), silicone, and neoprene elastomers and a fluoroelastomer at room temperature were dipped into the solution at 150°C, drained of excess solution, dried, and baked

30 overnight in an oven at 250°C. Coatings on all elastomer substrates were shiny and well-adhered.

Separately, cured EPDM rubber was coated and dried as above, then baked at 177°C for about 2 hr. The coating was judged to be of good quality and well adhered to the EPDM.

Example 13

A 3 wt% solution identical to that of Example 9 was painted onto two pieces of polyimide film (Kapton® grade 300HN, Du Pont) at room temperature and dried in an oven for one hour at 200°C. The two pieces
5 were placed in a laboratory press with coated sides together and pressed at 300°C and 417 psig for 30 sec, then cooled to room temperature. Peel strength was measured in the range 0.2-0.3 lb/in. Without the coating, the pieces would not bond together.

A 5 wt% solution of the TFE/HFP copolymer used in Example 8
10 was prepared in Fluorinert® FC-70 as in Example 11 and cooled to room temperature. As in Example 10, a low-viscosity cloudy suspension resulted. This suspension was painted onto both sides of two pieces of commercial 0.25-mm TFE/HFP copolymer film (Teflon® FEP fluorocarbon film 1000A, Du Pont) and onto one side of each of two
15 pieces of polyimide film described above and of two pieces of highly-polished 0.2-mm aluminum film. The coatings were dried for one hour at 200°C. Laminates of the FEP film between the polyimide films and between the aluminum films were pressed at 300°C and 417 psig for 30 sec, then cooled to room temperature. Control laminates were prepared
20 with no coatings on the components. Peel strengths were measured at room temperature in a tensile testing machine. For the polyimide laminates, the coated sample had peel strength of 1.8 lb/in while the control could not be tested, exhibiting no bond and falling apart. For the aluminum laminates, the coated sample and the control had peel
25 strengths of 4.0 and 0.5 lb/in, respectively.

Example 14

A TFE/HFP copolymer with HFPI = 6.91 and $MV = 0.49 \times 10^3$ Pa·s as polymerized and the TFE/HFP copolymer of Example 8 treated with fluorine to reduce the acid end group population were used to
30 prepare 2.5 wt% solutions in $C_{14}F_{24}$ on a hot plate at approximately 130°C. The solutions, chrome sheets, and a doctor knife were preheated at 130°C in a circulating air oven. A thin wet film of each solution was drawn down onto separate chrome sheets in the oven using the doctor knife set to a 0.13-mm gap. After at least 15 min drying in the oven, the
35 coated sheets were further dried in an oven for 60 min at 250°C. The

kinetic coefficient of friction (COF) of each coated surface was measured at room temperature against a high density polyethylene (HDPE) countersurface. COF results were 0.16 for the unfluorinated coating and 0.13 for the coating of fluorine-treated resin, compared with 0.19 for
5 uncoated chrome and 0.11 for sintered PTFE against HDPE. Adhesion of both coatings to the chrome appeared to be very good.

Example 15

A 1 wt% solution of the as-polymerized TFE/HFP copolymer resin of Example 14 was prepared at 120°C and cooled to room
10 temperature. To improve their lubricity, 0.36-mm diameter stainless steel wires were coated as follows. Wires were degreased by immersion in 1,1,2-trichloro-1,2,2-trifluoroethane (CFC-113) for 5 min, air-dried, and dip-coated at room temperature in a tube with 3.2 mm inside diameter filled with the copolymer/solvent system. After air drying, the coated
15 wires were further dried in a circulating air oven for 10 min at 120°C followed by 60 min at 250°C. The coated wires appeared smooth when inspected under a microscope at 25x magnification. The wires felt lubricious, and the coatings did not appear to be removed by rubbing.

Example 16

20 A. The TFE/HFP copolymer resin of Example 15 was used to make 1, 2, 3, 4 and 5 wt% solutions in $C_{14}F_{24}$ by dissolving at about 120°C (1-3 wt%) or at about 140°C (4-5 wt%) with stirring. Upon cooling to room temperature without stirring, the 3-5 wt% solutions formed solid gels, the 2 wt% solution formed a loose but still flowable gel, and
25 the 1 wt% solution remained a low-viscosity copolymer/solvent system. Taken together with the results of Example 9, these observations suggest that the concentration limit at which systems remain stable and fluid at ambient temperature may vary with copolymer composition.

Identical solutions were cooled with continued stirring which was
30 stopped when solution temperature was close to ambient temperature. None of the solutions had gelled, and even the 5 wt% copolymer/solvent system was readily flowable. The viscosities of the 3-5 wt% systems were observed to increase with time at a rate which increased with concentration. Over a period of days, the 3-5 wt%
35 systems increased in viscosity until they could be described as loose gels.

None of them formed the solid gels resulting from the quiescent cooling as described above. These loose gels were easily broken up by stirring, and the restirred systems gradually returned again to the loose gel state. Little or no change with time was observed in the 1-2 wt%

5 copolymer/solvent system.

The 3 wt% copolymer/solvent system cooled with stirring was used at room temperature to coat a chrome sheet also at room temperature using the doctor knife set to a 0.25-mm gap. The wet film was dried at room temperature overnight, then heated in an oven for 30
10 min at 275°C. The coating was observed to be smoother than the coatings of Example 14 prepared at elevated temperature.

B. Example 16A shows the beneficial effect of agitating the copolymer solution made by dissolving the copolymer in the solvent at an elevated temperature as it is cooled and becomes a
15 copolymer/solvent system during cooling, namely the viscosity is reduced, and if the concentration of copolymer were such as to cause gelling of the system during cooling to room temperature, the agitation also prevents the gelation, whereby the fluid, stable copolymer/solvent system is present at room temperature.

20 Example 16B discloses a further improvement in the process of the making of a fluid, stable copolymer/solvent system of the new TFE/HFP copolymers disclosed herein. As stated above, during the cool-down accompanied by agitation, the polymer/solvent system of reduced viscosity forms from the solution. If the agitation were stopped
25 when the system reaches room temperature as in the case of Example 16A, the viscosity of the system can increase upon standing at room temperature. It has been discovered that when the system is agitated additionally after it reaches room temperature, this further reduces the viscosity of the system. When the agitation is discontinued and the
30 system is stored at room temperature, the system may not undergo any significant increase in viscosity, i.e., its viscosity is stabilized.

Alternatively, the viscosity may increase with standing of the system, but the original lower viscosity can easily be restored by agitation. The agitation of the solution and polymer/solvent system can conveniently

be carried out by stirring or other means which applies shear to the entire body of fluid so that localized viscosity increase cannot occur.

To demonstrate this improvement, three solutions of partially crystalline TFE/HFP copolymer (HFPI of 8.8 and melt viscosity of 1.18×10^3 Pa·s) were prepared by adding the copolymer slowly to $C_{14}F_{24}$ solvent while stirring, followed by heating of the mediums in an oil bath at about 140°C with continued stirring until the polymer dissolved to form 5 wt%, 6 wt%, and 7 wt% solutions of the copolymer. These solutions were then allowed to cool while being stirred. The 5 wt% solution was stirred during cool-down with a magnetic stirrer providing the agitation. This stirrer did not have sufficient torque to stir the other solutions which exhibited greater tendency to thicken during cool-down. The 6 wt% solution was stirred with an overhead air motor stirrer and the 7 wt% solution was stirred with an overhead electric motor stirrer during cool-down, so that all three solutions were stable fluids when they reached room temperature. During this cool-down, the solutions became slightly cloudy, i.e., hazy. The stirring was continued for about 23 hours after the resultant copolymer/solvent systems reached room temperature. After discontinuance of this stirring the three mediums were each fluid, i.e., they were each capable of flowing with the application of little or no pressure and without any tendency to recover original shape after flow (deformation). In this example, the three systems exhibited fluidity by being pourable and being useful for dip coating of a substrate. The dip coating was carried out by dipping 0.3 mm diameter stainless steel wires at room temperature into the fluid systems. The resultant coating on each of the wires was dried at 45°C and baked at 275°C for 30 min to form a continuous coating on each of the wires. The 5 wt% copolymer system had a viscosity comparable to motor oil, and after storage of this system at room temperature for 7 months, the viscosity seemed unchanged. The 6 and 7 wt% copolymer systems also exhibited viscosity stability for a period of time, but viscosity slowly increased with standing. These systems did not gel, however, and their original lower viscosity could be restored by additional agitation. It is contemplated that this viscosity stability can be reached with shorter stirring time after reaching room temperature and

that stable, fluid copolymer/solvent systems containing greater amounts of copolymer, e.g. about 10 wt% thereof, can be obtained.

The results described in this Example 16 are also applicable to copolymer suspensions which have a tendency to settle upon standing at room temperature. The suspended particles of copolymer in the solvent can be from such source as copolymer gel formed during cooling, which is then broken up into very fine particles by the agitation during the cooling. Higher proportions of copolymer, as described earlier herein, can be present for the copolymer suspension as compared to the stable system.

Example 17

Solutions of the TFE/HFP copolymer resin of Example 8 were prepared in $C_{14}F_{24}$ at 120°C at concentrations of 0.15, 0.30, 0.75, 1.5 and 3.0 wt%, and were used at 120°C in the following coating work. A silicon wafer was scribed, cut into pieces about 2.5 cm square, cleaned with a soak in methylene chloride, rinsed with methanol, and dried in a vacuum oven at 150°C. A silicon square was immersed in each of the solutions maintained at 120°C, held for 30 min, and then withdrawn from the solution at a speed of 2 cm/min. The coated squares were dried for 15 min on a hot plate in air at 120°C. Thicknesses of the resulting films were measured by ellipsometry [Macromolecules 24, 5948 (1991)] using a Spectroscopic Ellipsometer (Sopra), and the quality of the surfaces was assessed by contact angle measurement with water [G. M. Bartenev and V. V. Lavrentev, Friction and Wear of Polymers, Tribology Series, 6, Elsevier (1981)]. As shown by the results in Table 3, low surface energy films as thin as 57 angstroms were made. Characterization of the wafer coated with the 0.15 wt% solution by atomic force microscopy [Science News 135, 200 (1989)] indicated that coating coverage was probably incomplete, based on detection of regions with surface smoothness characteristic of a bare silicon wafer. The observations suggest that concentrations of at least about 0.5 wt% are needed by this coating technique and on this particular substrate to achieve film surfaces that are fully characteristic of the copolymer. The silicon squares coated with the three most concentrated solutions were

heated again for 5 min on a hot plate at 204°C with no significant change in coating film thickness.

Table 3. Properties of Dip-Coated Films on Silicon

5		Contact \angle	Contact \angle	Thickness
	<u>Conc. (wt%)</u>	<u>Advancing</u>	<u>Receding</u>	<u>(angstrom)</u>
	Uncoated Si	47°	16°	—
	0.15	114°	58°	57
	0.30	115°	65°	63
10	0.75	117°	95°	197
	1.5	114°	93°	505
	3.0	116°	94°	835

Example 18

15 A 3 wt% solution of TFE/HFP copolymer in C₁₄F₂₄ identical to that of Example 18 was used to apply coatings on 5.1-cm diameter silicon wafers by spin coating. The spinning stage of a spin coater was enclosed in a chamber controlled at an interior air temperature of about 105°C. A small quantity, about 1-2 ml, of the solution maintained at
20 100°C was placed in the center of the disk at rest with a pipette, and the disk was then spun at chosen speed. The disk was spun for about 2 min which assured that the coating was dry, removed from the chamber and cooled to room temperature, and the copolymer film thickness was then measured by ellipsometry. Spinning speeds and resultant film
25 thicknesses are shown in Table 4.

Table 4. Summary of Spin Coating Experiments

<u>Expt.</u>	<u>Spinning Rate (rpm)</u>	<u>Film Thickness (angstrom)</u>	
		<u>Center</u>	<u>Edge</u>
1	500	652	672
2	750	*	369
3	850	80	80
4	1000	*	125
5	2000	180	285

* Not uniform and unable to measure.

Example 19

The TFE/HFP copolymer resin of Example 2 was tested as an extrusion process aid by the evaluation procedure described in the introduction to the examples. Results of the extrusion experiments are summarized in Table 5. Comparison of Δp_2 with Δp_1 shows that the fluoropolymer additive retains its exceptional effectiveness even when the antiblock is present. As indicated by the last column, T_p ranged from slightly below to about 25°C above $T_m(\text{end})$.

The same resin was also isolated from the dispersion by shear coagulation at 88°C. When evaluated as a processing aid, the dry copolymer powder from 88°C coagulation was significantly less effective, with Δp_2 in the range of only 27-40% for the three test temperatures. This is interpreted as an indication that the resin agglomerates were not as readily dissociated upon incorporation into the polyolefin as was the product of coagulation at lower temperature.

Table 5. Extrusion Test Results for Example 19

<u>Sample Coagulated at 20°C</u>			
<u>T_p (°C)</u>	<u>Δp_1 (%)</u>	<u>Δp_2 (%)</u>	<u>$T_m(\text{end}) - T_p$ (°C)</u>
195	47.3	47.0	6
210	53.0	51.0	- 9
225	52.0	49.8	- 24

Example 20

A series of TFE/HFP copolymers prepared generally by the methods of Examples 1 and 2 with variations in the details of ingredients and amounts charged, of the reaction conditions, and of the method of isolation had the properties listed in Table 6. These materials were tested at temperatures T_p shown in the table by the extrusion procedure described above in the introduction to the examples. TFE/HFP copolymer resin concentration was 500 or 1000 ppm. No systematic variation of performance with TFE/HFP resin concentration was in this range was discerned, so values are not presented. Values of Δp_1 and Δp_2 were calculated from the raw data and are plotted against $T_m(\text{end}) - T_p$ in Figures 3 and 4, respectively. The data for the resin of Example 1 are presented as sample No. 7 in Table 6 and are included in the plots. The greatest effectiveness of the fluoropolymer is at values of $T_m(\text{end})$ near T_p , i.e., for $T_m(\text{end}) - T_p$ near zero. Effectiveness extends to positive values of $T_m(\text{end}) - T_p$, indicating that the fluoropolymer need not be completely melted as taught by Blatz, U.S. 3,125,547.

Table 6.
Properties and Test Temperatures for TFE/HFP Copolymers of Ex. 20

No.	HFPI	T _m (peak) (°C)	T _m (end) (°C)	MV (10 ³ Pa.s)	T _p (°C)
1	7.60	191	234	0.34	225,260
2	8.49	170	203	0.35	204,230
3	6.91	185	225	0.49	235,260
4		169	210	0.52	204,230,260
5		166	200	0.54	204,230
6	7.80	177	245	0.56	204,218,250
7	8.87	171	204	0.59	204,220,250,260
8		194	226	0.68	204,230,250
9		187	217	0.69	205,230
10	7.61	184	214	0.76	220,230
11	6.42	204	243	1.01	204,230,250
12		184	220	1.04	204,218,250
13		181	228	1.38	230,240
14	7.75	183	217	1.40	220,230,260
15	7.37	197	230	1.70	204,250
16		192	225	1.93	230,260
17		198	238	2.25	205,250,260
18	7.56	178	215	3.51	230,260
19		205	248	3.73	204,250,260

Example 21

- 5 A TFE/HFP copolymer prepared generally by the procedure of Example 1 and having HFPI = 8.52, T_m(peak) = 165°C, T_m(end) = 203°C, and MV = 1.0 x 10³ Pa.s was evaluated as a processing aid at T_p = 225°C by the general procedure except that talc (ABT2500, Pfizer Minerals, Pfizer, Inc.) was sometimes used as antiblock agent instead of silica.
- 10 Measurements were taken over a TFE/HFP copolymer resin concentration range of 100-1000 ppm, but in two instances operation at 1000 ppm was preceded by operation without antiblock at a TFE/HFP copolymer resin concentration of 10% for 5 minutes or 25% for 3 minutes. When used as antiblock agent, talc concentration was 5000
- 15 ppm. Results in Table 7 show that the TFE/HFP copolymer is uniformly effective over a broad concentration range in the absence of antiblock and with talc as antiblock agent, and that it is less effective below 300 ppm with silica as antiblock agent. It was observed that the time to

reach equilibrium extrusion conditions varies with TFE/HFP copolymer concentration. Equilibration was slow at 100 ppm. Equilibration rate at 300 ppm was intermediate and almost equal to the rate at 1000 ppm. Preliminary operation at 10% and at 25% resulted in much faster equilibration.

Table 7. Extrusion with Different TFE/HFP Resin Concentrations

	<u>Conc. (ppm)</u>	<u>Antiblock</u>	<u>Δp_1 (%)</u>	<u>Δp_2 (%)</u>
10	100	Silica	53.5	26.2
	200	Silica	54.9	37.5
	200	Talc	54.5	52.7
	300	Silica	54.5	45.3
	1000	Silica	50.3	51.9
15	1000 ^a	Talc	52.5	53.8
	1000 ^b	Silica	53.1	52.4

^a 10% for 5 min without antiblock, then 1000 ppm.

^b 25% for 3 min without antiblock, then 1000 ppm.

Comparative Example A

The extrusion evaluation procedure outlined in the introduction to the examples was followed using 1000 ppm of an elastomeric copolymer of vinylidene fluoride (VF₂) and HFP made by the process of U.S. Patent 2,968,649 as the fluoropolymer process aid. Molar composition of the elastomer was approximately VF₂/HFP = 78/22 and glass transition temperature T_g was about -23°C. This polymer is similar to that used by Blatz (U.S. 3,125,547) in several of his examples. Test temperature was 250°C. A single test temperature was employed because the elastomer has no crystalline melting point and all reasonable polyolefin processing temperatures are well above T_g. Test results were $\Delta p_1 = 33\%$ and $\Delta p_2 = 39\%$. Although the performance of this fluoropolymer did not suffer when antiblock was added, the level of performance was substantially below the better range of performance exhibited by the polymers of Example 20 shown in Figures 3 and 4.

Comparative Example B

Perfluorohexadecane, a low molecular weight TFE homopolymer with $T_m(\text{peak}) = 128^\circ\text{C}$ and $T_m(\text{end}) = 140^\circ\text{C}$, was evaluated as a processing aid at 1000 ppm at $T_p = 150^\circ\text{C}$ and 204°C . Δp_1 was 1.8% and
5 1.1%, respectively. These values are too low to be of interest, so measurement of Δp_2 was omitted. Based on T_m , this polymer is judged to be very similar to that tested by Blatz in his Example III.

Comparative Example C

To test the possibility that the fluoropolymer of Comparative
10 Example B melted too far below normal T_p for LLDPE to be effective, another low molecular weight TFE homopolymer with $T_m(\text{peak}) = 190^\circ\text{C}$ and $T_m(\text{end}) = 204^\circ\text{C}$ (perfluorotetracosane) was evaluated at 1000 ppm at $T_p = 185^\circ$, 204° , and 225°C . $\Delta p_1 = 9.7\%$, 4.4% , and 1.2% , respectively. Measurement of Δp_2 was again omitted. Although this
15 TFE homopolymer has T_m comparable to some of the TFE/HFP copolymers of Example 20, it does not exhibit the outstanding performance of those copolymers for T_p close to T_m .

The melt viscosities of the TFE homopolymers used in Comparative Examples B and C are much less than $0.1 \times 10^3 \text{ Pa}\cdot\text{s}$, i.e. the
20 melt viscosities are so low as not to be measurable by the method used to measure the melt viscosities disclosed herein.

Example 22

A portion of the TFE/HFP copolymer resin identified as No. 19 in Table 6 was treated with fluorine gas as described above. Infrared
25 analysis indicated that the combined concentration of carboxylic acid and acid fluoride end groups was reduced from $369/10^6 \text{ C atoms}$ before fluorination to $40/10^6 \text{ C atoms}$ by a single fluorine treatment and then to $20/10^6 \text{ C atoms}$ by a second fluorine treatment. The original and fluorine-treated resins were tested at 260°C by the extrusion procedure
30 described in the introduction to the examples. Results summarized in Table 8 show that fluorine treatment does not impair the effectiveness of the fluoropolymers of this invention as processing aids, contrary to the teachings of U.S. Patent 5,132,368 for the polymers studied therein.

Table 8. End Group Population and Processing Aid Performance

	<u>Ends (ppm)</u>	<u>Δp_1 (%)</u>	<u>Δp_2 (%)</u>
	369	60.6	48.6
	40	62.7	62.8
5	20	65.4	63.9

Example 23

The TFE/HFP copolymer of Example 9, which had $T_m(\text{peak}) = 173^\circ\text{C}$, $T_m(\text{end}) = 204^\circ\text{C}$, and an acid end group population of $850/10^6$ C atoms, was tested as a processing aid at 1000 ppm and $T_p = 204^\circ\text{C}$ by the procedure described in the introduction to the examples except that 5000 ppm of talc was used as antiblock agent. Under these conditions, $\Delta p_1 = 50.0\%$ and $\Delta p_2 = 50.8\%$. Various samples of this copolymer resin were treated with fluorine to reduce the population of carboxylic acid and acid fluoride ends to the range $49\text{--}244/10^6$ C atoms. These treated samples were evaluated in the extrusion test at 60 rpm only, for which results had been found to approximate the average over the four screw speeds spanning the 30-120 rpm range. Results were tightly bunched in the ranges $\Delta p_1 = 47.6\text{--}54.2\%$ and $\Delta p_2 = 47.2\text{--}53.4\%$ and showed no systematic variation with functional end group population.

Comparative Example D

Four different perfluoroelastomers were evaluated as processing aids at a concentration of 200 ppm and at $T_p = 204^\circ\text{C}$ by the general procedure described above. The perfluoroelastomers were copolymers of TFE and PMVE with different curesite monomers prepared according to the patent references given in the following Table 9 along with test results.

Table 9. Extrusion Results for Perfluoroelastomers

	<u>Sample</u>	<u>U.S. Patent</u>	<u>Δp_1 (%)</u>	<u>Δp_2 (%)</u>
30	A	3,467,638	36	3
	B	4,035,565	46	33
	C	4,281,092	29	4
	D	4,529,784	28	29

These results show that non-crystalline perfluoropolymers do not exhibit the exceptional performance of the highly-fluorinated partially-crystalline copolymers of this invention.

Example 24

- 5 A partially crystalline TFE/PMVE copolymer was prepared in a shaker tube generally according to the procedures of U.S. Patent 3,132,123 with water as the polymerization medium and using 1,4-diiodoperfluorobutane as chain transfer agent. This polymer contained 33 wt% PMVE and had $T_m(\text{peak}) = 200^\circ\text{C}$, $T_m(\text{end}) = 225^\circ\text{C}$,
10 and $MV = 6.5 \times 10^3 \text{ Pa}\cdot\text{s}$ by ASTM D-1218 at 250°C . When evaluated as a processing aid at 500 ppm and $T_p = 250^\circ\text{C}$, $\Delta p_1 = 47\%$. Δp_2 was not measured. The value $\Delta p_1 = 47\%$ fits nicely on the plot in Figure 3, indicating that this perfluorinated polymer functions much like
15 TFE/HFP copolymers if melting and processing temperature relationships are the same. Furthermore, this result and the results of Comparative Example D taken together indicate that a fluoropolymer with very high fluorine content must also be partially crystalline to yield exceptional performance as a process aid.

Comparative Example E

- 20 A sample of TFE/HFP copolymer prepared generally by the method of U.S. Patent 2,946,763 with $HFPI = 5.47$, $T_m(\text{peak}) = 241^\circ\text{C}$, and $T_m(\text{end}) = 305^\circ\text{C}$ was tested as a processing aid. Copolymer powder concentration was 1000 ppm and $T_p = 225^\circ$, 250° , and 275°C . $\Delta p_1 = 10\%$,
25 36% , and 42% , respectively. Antiblock was not tested at 225°C , but $\Delta p_2 = 29\%$ and 15% , respectively, for the other two temperatures. Placement of these data on Figures 3 & 4 suggests that the performance of this polymer may track the pattern discerned for the TFE/HFP copolymers of this invention, but that T_p would have to be undesirably high to realize comparable performance. This copolymer is nominally the same
30 as that used by Concannon in U.S. Patent 4,075,362.

Example 25

- A commercial TFE/HFP/ VF_2 terpolymer (Hostaflon® TFBX-7100, Hoechst) was tested as an extrusion processing aid by the evaluation procedure described in the introduction to the examples. For this test,
35 concentration was 1000 ppm and $T_p = 180^\circ$ and 225°C . Results were

$\Delta p_1 = 35.4$ and 48.9% and $\Delta p_2 = 30.8$ and 44.6% , respectively. DSC analysis of the terpolymer yielded $T_m(\text{peak}) = 165^\circ\text{C}$ and $T_m(\text{end}) = 192^\circ\text{C}$, while NMR analysis showed composition to be about TFE/HFP/VF₂ = 51/16/32 by weight. This composition translates to a
5 hydrogen content in the polymer of about 1 wt%. The result indicates that the surprisingly superior performance as a processing aid when $T_m(\text{end})$ is close to T_p extends to highly-fluorinated partially-crystalline polymers that are not perfluorinated.

Example 26

10 A 1.5 wt% solution of the TFE/HFP copolymer of Example 8 in C₁₄F₂₄ was used. A golf ball injection molding mold was heated to approximately 204°C in an air oven and then removed from the oven. While still warm, the mold surfaces that contact polymer were painted with the copolymer solution. The mold pieces were air cooled and were
15 then placed in injection molding service, molding ionomer resin around insert cores. The mold was operated 5 days/week for approximately 12 weeks with an average mold cycle time of 70 sec or less without the need to renew the TFE/HFP copolymer coating for adequate release. In previous experience molding the same article under the same molding
20 conditions but using a mold release lubricant, cycle time was longer and it was necessary to reapply the mold release lubricant every 15-30 cycles. It was not necessary to use the lubricant after the mold was coated with the TFE/HFP copolymer.

Example 27

25 The TFE/HFP copolymer of Example 8 was used to mold a plaque approximately 15 cm square and 1 mm thick. A brass frame of appropriate dimensions was placed on a piece of polyimide film (KAPTON®, DuPont Company). Copolymer powder (65 g) was placed in the square opening of the frame and was distributed uniformly. The
30 filled frame was covered with another piece of polyimide film, and the assembly was placed between the platens of a laboratory press heated to 203°C. The press was closed to make slight contact with the assembly, held in that position for 5 min, then fully closed. After 5 min at 10,000 lb (4545 kg) load, the assembly was removed from the hot press and was
35 immediately transferred to another press with water-cooled platens at

25°C. When cool, the polyimide film was stripped off the assembly and the plaque was removed from the frame. The plaque was visually colorless, clear, and free from haze except for a small region near one edge. Seventeen additional plaques molded by the same procedure
5 were discerned to have no haze by inspection with the unaided eye.

CLAIMS

1. A partially crystalline copolymer of tetrafluoroethylene and hexafluoropropylene having a hexafluoropropylene index (HFPI) in the range 6.4 to about 9.
- 5 2. The copolymer of Claim 1 wherein the melt viscosity (MV) of said copolymer is in the range of 0.1×10^3 to 10×10^3 Pa·s.
3. A polymer blend composition having improved processibility, comprising a polyolefin and an effective amount, to improve processibility, of a partially-crystalline fluoropolymer containing no
10 more than 2 wt% hydrogen, having a melt viscosity from about 0.1×10^3 to 20×10^3 Pa·s, and having the end of crystalline melting, $T_m(\text{end})$, in the range from about 170°C to about 265°C.
4. The polymer blend composition of Claim 3 wherein said fluoropolymer is the copolymer of Claim 1.
- 15 5. A process comprising melt extruding the polymer blend composition of Claim 3, wherein the end of the crystalline melting range, $T_m(\text{end})$, of the fluoropolymer is in the range from about 40°C below to about 25°C above the extrusion temperature of the polyolefin.
6. A solution of the copolymer of Claim 1 in a highly fluorinated
20 cycloalkane or aromatic solvent, having a copolymer concentration up to about 30 wt%.
7. The solution of Claim 6 wherein the copolymer has a viscosity (MV) of from about 0.1×10^3 to about 10×10^3 Pa·s.
8. A fluid, stable copolymer/solvent system of the copolymer of
25 Claim 1 in highly-fluorinated cycloalkane or aromatic compound wherein the copolymer concentration is from about 0.1 to about 10 wt%.
9. A suspension of the copolymer of Claim 1 in a highly-fluorinated cycloalkane or aromatic solvent, having a copolymer concentration of at least 0.1 wt%.
- 30 10. A gel comprising a highly-fluorinated cycloalkane or aromatic solvent and the copolymer of Claim 1.
11. Process for making a fluid, stable copolymer/solvent system or a copolymer suspension in a solvent, wherein the copolymer is the copolymer of Claim 1 and wherein said solvent is highly-fluorinated
35 cycloalkane or aromatic compound, and the copolymer concentration is

at least 0.1 wt% comprising dissolving said copolymer in said solvent at elevated temperature, cooling the resultant solution, agitating said solution during said cooling, whereupon during said cooling said solution forms said system or said suspension, said system or
5 suspension having at least a lower viscosity than if said agitation had been omitted.

12. Process of Claim 11 and additionally agitating said system or suspension after reaching room temperature to further reduce the viscosity of said system or suspension.


10 13. A coated article comprising a substrate coated with a coating, wherein the coating comprises the copolymer of Claim 1.

14. The coated article of Claim 13 wherein the copolymer has a melt viscosity (MV) of from about 0.1×10^3 to about 10×10^3 Pa·s.

15 15. A method of bonding two articles together, comprising bringing two articles, at least one of which is a coated article comprising a substrate coated with a coating wherein the coating comprises the copolymer of Claim 1, into conforming contact, heating at least the region of contact above the melting temperature of the copolymer, and applying pressure for sufficient time to form the bond.


1/4

FIG. 1




2/4

FIG. 2




3/4

FIG. 3



4/4

FIG. 4



INTERNATIONAL SEARCH REPORT

Internat: Application No

PCT/US 93/07789

A. CLASSIFICATION OF SUBJECT MATTER
IPC 5 C08F214/26 C09D127/18

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 5 C08F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US,A,3 062 793 (H.S. ELEUTERIO) 6 November 1962 see column 2, line 9 - line 14; claim 1 ---	1
X	US,A,2 598 283 (W.T. MILLER) 23 October 1947 see column 3, line 64 - column 4, line 32 ---	1
A	US,A,3 132 124 (M.J. COUTURE) 5 May 1964 -----	1

☐ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
"E" earlier document but published on or after the international filing date
"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
"O" document referring to an oral disclosure, use, exhibition or other means
"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

11 November 1993

Date of mailing of the international search report

24. 11. 93

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

GLIKMAN, J

INTERNATIONAL SEARCH REPORT

Information on patent family members

Internat'l Application No

PCT/US 93/07789

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US-A-3062793		NONE	
US-A-2598283		NONE	
US-A-3132124		FR-A- 1336181 GB-A- 998498	